


## Technical Datasheet


# Cromophtal® Violet L 5805

Violet pigment with very high color strength, recommended for high-performance industrial coatings

Colour Index™	P.V. 23   51319
Chemical Class	Dioxazine



1/3 Standard Depth  
Alkyd / Melamine



1/25 Standard Depth  
Alkyd / Melamine

### Weathering

#### Air-drying alkyd

1/3 Standard Depth	4 - 5
1/25 Standard Depth	4 - 5
1/200 Standard Depth	4 - 5

### Physical Properties

Bulk density	1,5 kg/L	Specific surface	99 m <sup>2</sup> /g
Bulk volume	2,4 L/kg	Thermal resistance	200 °C
Oil absorption	60 g/100g		

## Chemical Fastness

of FullShade in Alkyd / Melamine

Substance	value (GS)
-----------	------------

Alkali (2% NaOH)	5
------------------	---

Acid (2% HCl)	5
---------------	---

### Suitability in Medium

Air-drying alkyd	●
------------------	---

Amine-curable	●
---------------	---

Acid-curable	●
--------------	---

Acrylic / isocyanate	●
----------------------	---

Water-based	●
-------------	---

Baking finishes	●
-----------------	---

### Suitability in Industry

Automotive	○
------------	---

Coil	○
------	---

Decorative	●
------------	---

General Industrial	●
--------------------	---

Powder	○
--------	---

Wood	○
------	---

### Solvent Fastness

Butyl acetate	4
---------------	---

Ethyl acetate	4
---------------	---

DI Water	5
----------	---

Xylene	4 - 5
--------	-------

Ethanol	4 - 5
---------	-------

Butanol	4 - 5
---------	-------

Ethylene glycol	4
-----------------	---

## Note

Although the information presented here is believed to be reliable, Sun Chemical Corporation makes no representation or guarantee to its accuracy, completeness or reliability of the information. All recommendations and suggestions are made without guarantee, since the conditions of use are beyond our control. There is no implied warranty of merchantability or fitness for purpose of the product or products described herein. In no event shall Sun Chemical Corporation be liable for damages of any nature arising out of the use or reliance upon the information. Sun Chemical Corporation expressly disclaims that the use of any material referenced herein, either alone or in combination with other materials, shall be free of rightful claim of any third party including a claim of infringement. The observance of all legal regulations and patents is the responsibility of the user.

Greyscale (GS) 5 (best) - 1 (worst); Blue Wool Scale (BWS) 8 (best) - 1 (worst)

● suitable      ● potential suitable      ○ not suitable